



Elsanek
Ref. **SpitProtect 140**

[SpitProtect]
TECHNOLOGY

Kaki 2324CP

Gris/Grey 429CP

Blanco/White



Composición / *Composition*

40%Olefine
40%PES
19%PU
1%Antistatic (LATEX FREE)

Peso / <i>Weight</i> (gr/m ²)	140 ± 5%	UNE 40-339-76
Ligamento / <i>Ligament</i>	Piqué Knited	
Ancho / <i>Width</i> (cm)	190 ± 2	
Encogimiento al lavado 75°C / <i>Washing shrinkage 75°C</i>	3%	EN 6330/15797
Resist. a penetración de agua / <i>Water Penetration Resistance</i> (cm/H ₂ O)	>1000	EN20811
Antiestático / <i>Antistatic</i> (Ω)	Pass	EN1149/3
Protección contra agentes biológicos / <i>Protection against biological agents</i>	Pass (150 lavados/ <i>washes</i>)	EN14126
Protección contra agentes químicos / <i>Protection against chemical agents</i>	Pass (150 lavados/ <i>washes</i>)	EN14605
Antiácido / <i>Antiacid</i>	Clase 3 / <i>Cass 3</i>	EN13034 (Ácido Sulfúrico/Hidróxido Sódico)

Instrucciones de lavado / *Washing instructions:*



Temperatura lavado:
recomendado a 40°C / max. 75°C
Washing temperature:
recommended at 40°C / max. 75°C



No permite el uso de lejía
Bleach NOT allowed



Secado con secadora: Temperatura recomendada: 40°C (max. 40°C). Duración: máximo 20 minutos + 5 minutos en frío (en función de la carga). / **Secado con tunel de secado:** Temperatura recomendada: 70°C (max. 70°C).

Drying using a drying machine:
Recommended temperature: 40°C (max. 40°C). Duration: maximum 20 minutes + 5 minutes cold wash (depending on the load). / **Drying using tunnel:** *Recommended temperature: 70°C (max. 70°C).*



No planchar
Do not iron



Se recomienda plegar o colgar la pieza de ropa después del proceso de secado para reducir las arrugas.
It is recommend to fold or hang the garments after finishing the drying process in order to reduce the amount of wrinkles.