



Elsanek
Ref. **Olefine 170**

olefine
TECHNOLOGY

Negro/Black 6C

Azul/Blue 540CP

Gris/Grey 429CP

Blanco/White



Composición / *Composition*

99% Olefine + 1% Antistatic

Peso / *Weight* (Grams/m²)

170 ± 5%

UNE 40-339-76

Ligamento / *Ligament*

Punto Liso / Knit

Ancho / *Width* (cm)

190 ± 1

Estallido / *Bursting Resistance*

>500 kPa

EN ISO 13938-1:2019

Pilling Martindale

Nulo / Null

EN12945-2

Antistatic

Pass

EN 1149-5



Reciclable / *Recyclable*

Imprescindible fornituras de PP (Polipropileno) en prenda.
Essential thermoplastic PP (Polirpopilene) fittings in garment.

Instrucciones de lavado / *Washing instructions:*



Temperatura lavado:
recomendado a 40°C / max. 75°C
*Washing temperature:
recommended at 40°C / max. 75°C*



Permite el uso de lejía, cloro o cualquier otro detergente.
It allows the usage of bleach, chlorine or any other detergent



Secado con secadora: Temperatura recomendada: 40°C (max. 40°C). Duración: máximo 20 minutos + 5 minutos en frío (en función de la carga). / **Secado con tunel de secado:** Temperatura recomendada: 70°C (max. 70°C).

Drying using a drying machine:
Recommended temperature: 40°C (max. 40°C). Duration: maximum 20 minutes + 5 minutes cold wash (depending on the load). / **Drying using tunnel:** Recommended temperature: 70°C (max. 70°C).



No planchar
Do not iron



Se recomienda plegar o colgar la pieza de ropa después del proceso de secado para reducir las arrugas.
It is recommend to fold or hang the garments after finishing the drying process in order to reduce the amount of wrinkles.